



สีรองพื้นไม้อลูมิเนียม เป็นสีรองพื้นไม้คุณภาพเยี่ยม ที่มีองค์ประกอบของโพลีโอะเรซินสังเคราะห์ และผงอลูมิเนียม มีคุณสมบัติพิเศษที่สามารถป้องกันกาเกิดเชื้อรา เหมาะสำหรับพื้นผิวไม้ทุกประเภท โดยเฉพาะไม้ที่มียางไม้มาก และไม้ที่เคยเคลือบน้ำยารักษาเนื้อไม้มาก่อน สีรองพื้นไม้อลูมิเนียม จะช่วยป้องกันยางไม้มิให้ซึมออกมาทำลายความสวยงามของสีทับหน้า

- มีส่วนผสมของอลูมิเนียมป้องกันการลอ่ยตัวของยางไม้
- ป้องกันการเกิดเชื้อรา
- ช่วยป้องกันไม่ให้ยางไม้ซึมออกมายังสีทับหน้า
- ไม่ผสมสารตะกั่ว และสารปรอท

ข้อมูลทางเทคนิคและคุณสมบัติของฟิล์มสี

ประเภทสี	สีรองพื้นไม้
ลักษณะฟิล์มสี	เนียน
ขนาดบรรจุ	1 ยูเอสแกลลอน
เฉดสี	สีเทาเงิน
เนื้อสีโดยปริมาตร	ประมาณ 50 - 60%
ระยะเวลาแห้งสัมผัส	4 ชั่วโมง
ระยะเวลาทาทับ	8 - 10 ชั่วโมง
การครอบคลุมพื้นที่ตามทฤษฎี	40 - 50 ตร.ม./เที่ยว/แกลลอน
*พื้นที่ครอบคลุมเป็นค่าทางทฤษฎี อาจแตกต่างจากการใช้งานจริงไม่เกิน 20%	

วิธีการใช้งาน

เครื่องมือ และอุปกรณ์ในการใช้งาน	แปรง
การผสมก่อนใช้งาน	สามารถใช้ได้ทันที หรือเติมน้ำยาผสมสีน้ำมันดูลักซ์ (T850-411) 1 ส่วน ต่อสี 10 ส่วน (ไม่เกิน 10%)
การทำความสะอาด	ล้างทำความสะอาดอุปกรณ์ด้วย น้ำยาผสมสีน้ำมันดูลักซ์ (T850-411) ทันทีหลังการใช้งาน

ระบบการทาสี

พื้นผิวที่จะทาต้องแห้ง สะอาด ปราศจากคราบไขมันและฝุ่นผง ควรขัดลอกพื้นผิวเก่าด้วยกระดาษทรายก่อนทาทับด้วยสีรองพื้น สำหรับพื้นผิวอลูมิเนียม สแตนเลส สังกะสี ควรทำความสะอาดให้ปราศจากคราบไขมัน หรือให้ปฏิบัติตามคำแนะนำของผู้ผลิต

การเตรียมพื้นผิว สำหรับพื้นผิวไม้

- พื้นผิวไม้ใหม่
- พื้นผิวไม้เก่า

ในกรณีที่ไม่เคยอยู่ในสภาพดี

ในกรณีที่ไม่เคยเสื่อมสภาพ

- สำหรับงานไม้ทุกประเภท

ขัดผิวให้เรียบ แล้วทำความสะอาดพื้นผิวให้ปราศจากคราบไขมันและฝุ่นผง

ลูบผิวให้เรียบด้วยกระดาษทรายเพื่อเสริมการยึดเกาะ แล้วทำความสะอาดผิวให้ปราศจากคราบไขมันและฝุ่นผง ให้ขัดลอกสีเดิมที่เสื่อมสภาพออก แล้วทำความสะอาดผิวให้ปราศจากคราบไขมันและฝุ่นผง

ถ้ามีรอยแตกหรือรู ให้อุดด้วยสีโป๊วดูลักซ์ อะคริลิก พิลเลอร์ 1040 และเพื่อป้องกันการที่สมบูรณ์แบบ หากมีหัวตะปู ให้แถมสีรองพื้นกันสนิมตามชนิดหัวตะปู

การทาสีรองพื้น

ทาสีรองพื้นไม้ดูลักซ์ อลูมิเนียม 1 เที่ยว ด้วยแปรง โดยใช้วิธีทาแบบไขว้ไปมา เพื่อให้สีรองพื้นซึมเข้าไปในเนื้อไม้ ทั้งระยะเวลาให้แห้งสนิทหรือประมาณ 8 - 10 ชั่วโมง ก่อนทาสีทับหน้า

การทาสีทับหน้า

ทาสีทับหน้าด้วย สีน้ำมันเคลือบเงา ดูลักซ์ กลอส ฟินิช หรือ ดูลักซ์ ซิลคี่วูด อย่างน้อย 2 เที่ยว ด้วยแปรงทาสี ลูกกลิ้งขนเรียบหรือสเปร์รี่ โดยทิ้งเวลาให้ชั้นแรกแห้งสนิทก่อนทาทับหน้าชั้นถัดไปประมาณ 8 - 10 ชั่วโมง



ISO 9001 QMS03026/630
ISO 14001 EMS05021/198
OHSAS 18001 OHSAS04016/079
TIS 18001 OHS01013/028



Dulux Aluminium Wood Primer

For Exterior and Interior



Dulux Aluminium Wood Primer is a high quality wood primer with oleoresins based and aluminium pigment. Special feature on fungus resistance. A general purpose primer for wooden surfaces and acts as an efficient sealer to wood work coated with bitumen or to selected paint system.

- Aluminium pigment to prevent non-leaving gum from wood
- To prevent wood bleeding from underneath
- Fungus resistance
- Contains no added mercury

Technical Information & Paint Film Properties

Type of Paint	Aluminium Wood Primer
Finish	Sheen
Pack size	1 U.S. Gallons
Colour Offer	Silver gray
Volume Solids	50 - 60%
Touch Dry	4 hour
Recoat Dry	8 - 10 hour
Theoretical Coverage	40 – 50 Sq.m./coat/gallon

*Coverage is theoretical value and may differ from real application +-20%

Application

Application Method	Brush
Mixing Ratio	Ready to use. Can be thinned with 1 part of Dulux Quick Cut Solvent (T850-411) to 10 parts of the product (10%)
Cleaning Up	Clean all equipment with Dulux Quick Cut Solvent (T850-411C) immediately after used

Application System

Surface generally must be clean, dry and free from defective or poorly adhering material, dirt, grease, wax etc. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dusted off. For optimum performance new galvanized, aluminum and stainless steel surfaces should be cleaned and degreased. Then follow the instruction of manufacturer.

Surface Preparation : Wooden Surface

- *New wood* Rub down until smooth surfaces. Then clean surface to remove all grease and dirt.
- *Old wood* Rub down with abrasive paper for good adhesion of new paint. Then clean surface to remove all grease and dirt.
- *Good condition previously painted masonry* Thoroughly rub down till old paint and rust totally removed. Then clean surface to remove all grease and dirt.
- *Defective condition previously painted masonry* Apply 1 coat of Dulux Aluminium Wood Primer. It is best applied by brush with a crisscross motion using considerable pressure to promote paint penetration. Allow 8 - 10 hours drying prior applying top coat.

Priming

Coating

Apply at least 2 coats of Dulux Gloss Finish or Dulux Silkwood with brush, short hair roller or spray. Allow at least 8 - 10 hours drying between coat.



ISO 9001 QMS03026/630
 ISO 14001 EMS05021/198
 OHSAS 18001 OHSAS04016/079
 TIS 18001 OHS01013/028

The information in this datasheet is given to the best of our knowledge based on laboratory testing and for use recommendation. As the product is often used under conditions beyond our control, the company cannot guarantee anything only the quality of the product.

AkzoNobel Paints (Thailand) Ltd. (Former ICI Paints (Thailand) Ltd.) 34/5 Moo 1 Chaeng Watana Road, Klongklue, Pakkred Nonthaburi 11120
 Customer Service : Telephone (662) 572-8888 Fax (662) 572-8889 www.dulux.co.th, www.facebook.com/duluxthailand