



น้ำมันรักษาเนื้อไม้ คิวพรีโนล ทีก ออยล์ เป็นน้ำมันสีใสสูตรพิเศษ สำหรับทาเพื่อรักษาเนื้อไม้สักและเนื้อไม้ทุกประเภท ทั้งไม้ใหม่และไม้เก่า น้ำมันทีก ออยล์ มีคุณสมบัติช่วยทดแทนน้ำมันตามธรรมชาติของเนื้อไม้ที่สูญเสียไปเพราะแสงแดด สภาพอากาศ และการใช้งาน อีกทั้งยังมีคุณสมบัติในการป้องกันเชื้อรา เหมาะสำหรับเฟอร์นิเจอร์ไม้ทั้งภายนอกและภายใน ราวระเบียง ทางเดิน รั้วไม้ และอุปกรณ์ตกแต่งที่ทำจากไม้ทุกประเภท ไม่มีส่วนผสมของสารตะกั่วและสารปรอท

ข้อมูลทางเทคนิคและคุณสมบัติของฟิล์มสี

ประเภทสี	น้ำมันรักษาเนื้อไม้
ลักษณะฟิล์มสี	ไม่มีฟิล์มสี
ขนาดบรรจุ	3.5 ลิตร
เจดสี	ใส
ระยะเวลาแห้งสัมผัส	ไม่น้อยกว่า 4 ชั่วโมง
ระยะเวลาทาทับ	10 – 12 ชั่วโมง
การครอบคลุมพื้นที่ตามทฤษฎี	15 – 20 ตร.ม. / เที่ยว / ลิตร

*อัตราการปกคลุมพื้นผิวขึ้นอยู่กับชนิดและสภาพของพื้นผิว ปัจจัยที่มีผลต่อระยะเวลาแห้ง คือ อุณหภูมิ และความชื้นในอากาศ น้ำมันธรรมชาติในไม้ อาจมีผลทำให้น้ำมันรักษาเนื้อไม้แห้งช้าลงได้

วิธีการใช้งาน

วิธีการใช้งาน	แปรงหรือเครื่องพ่น
การผสมก่อนใช้งาน	ใช้ได้ทันทีหรือ หากต้องการเจือจาง ใช้ทินเนอร์เนกประสงค์ ไอ ซี ไอ คิวพรีโนล เจือจางไม่เกิน 5%
การทำความสะอาด	ล้างทำความสะอาดอุปกรณ์ทันทีหลังการใช้งานด้วยทินเนอร์เนกประสงค์ ไอ ซี ไอ คิวพรีโนล
ข้อแนะนำในการฉีดพ่น	ไม่แนะนำให้ฉีดพ่น

ระบบการทาสี

การเตรียมพื้นผิว สำหรับพื้นผิวไม้

- ไม้ที่ผ่านการย้อมไม้มาก่อน
- ไม้ที่ยังไม่ผ่านการย้อมไม้มาก่อน
- ไม้ใหม่
- ไม้เก่า
- ไม้ที่ผ่านการทาสีหรือลงน้ำยาชักเงามาก่อน
- ไม้แข็งที่ผ่านการย้อมสีและมีคุณภาพดี
- ไม้ที่อยู่ภายนอกอาคารหรืออยู่สภาพแวดล้อมริมทะเล

พื้นผิวจะต้องสะอาดแห้ง ปราศจากสิ่งย้อมไม้เดิมหรือคราบไขมันก่อนการทา ความชื้นไม่เกิน 14% ทาด้วยน้ำยารักษาเนื้อไม้ที่เหมาะสม (น้ำยารักษาเนื้อไม้ที่ไม่มีส่วนผสมของน้ำมันดิน) ทิ้งให้แห้งประมาณ 2-5 วัน ก่อนจะทาด้วยสีย้อมไม้ ไอ ซี ไอ คิวพรีโนล วัสดุเสตน ชนิดกึ่งเงา เช็ดด้วยทินเนอร์เนกประสงค์ ไอ ซี ไอ คิวพรีโนล เพื่อขจัดคราบน้ำมันธรรมชาติ หรือยางไม้ ก่อนการย้อมสี ขัดพื้นผิวที่กลายเป็นสีเทาออกให้หมดด้วยกระดาษทรายให้เหลือแต่ไม้ที่สะอาดและแห้ง ขัดหรือใช้เครื่องเป่าลมร้อน ลอกสีหรือน้ำยาชักเงาออกให้หมดถึงเนื้อไม้เดิม แล้วจึงเตรียมไม้เช่นเดียวกับไม้เปล่า ไม่แนะนำให้ใช้สารเคมีกัดสีหรือน้ำยาลอกสี ต้องการทำความสะอาดพื้นผิวได้ด้วยสารทำลายที่ เหมาะสมเสียก่อน เพื่อให้ได้ไม้ที่สะอาด ล้างและขัดด้วยทินเนอร์เนกประสงค์ ไอ ซี ไอ คิวพรีโนล เพื่อขจัดคราบน้ำมันและฝุ่นผงแล้วทิ้งให้แห้งก่อน การย้อมสี ตระปุกตัวที่ใช้ควรผ่านการชุบสังกะสี (กาลวาไนซ์) หรือใช้ตะปุกปลอดสนิม (Stainless Steel)

การทาสีทับหน้า

คนเนื้อสีให้ทั่วและเท่ากันก่อนการใช้งาน และหมั่นคนอยู่เสมอในขณะที่ใช้งาน ใช้แปรงทาตามเส้นลายไม้ โดยสม่ำเสมอ วางแผนในการทาต่อเนื่องเพื่อไม่ให้เกิดการทาสีซ้อน ในการทาสีย้อมไม้เที่ยวแรก ให้ทาเพียงเบาๆ เพื่อการซึมที่ดี หากทาหนาเกินไป สามารถเช็ดออกด้วยผ้าสะอาด ไม้ที่อยู่ภายในอาคารให้ทาสีย้อมไม้ ทั้ 2 เที่ยว สำหรับไม้ที่อยู่ภายนอกอาคารให้ทาสีย้อมไม้ทั้ 3 เที่ยว ไม่แนะนำให้ทาสีย้อมไม้ทั้ 3 เที่ยว ควรทิ้งให้สีย้อมวัสดุเสตน ชนิดกึ่งเงาแห้งสนิท (ทั้ 3 ชั่วโมง) ก่อนการย้อมสีทับในเที่ยวถัดไป ห้ามทาสีใน สภาพอากาศที่มีความชื้นสูง เช่น ก่อนหรือหลังฝนตกหรือระหว่างฝนตก ควรทาสีเที่ยวแรกบนชิ้นไม้ก่อนนำไปประกอบให้ทั้ทุกด้าน และทาสีทับอีกครั้งหนึ่ง เมื่อนำชิ้นไม้ไปติดตั้งแล้ว เพื่อให้ได้ความสม่ำเสมอของเนื้อสี



ISO 9001 QMS03026/630
ISO 14001 EMS05021/198
OHSAS 18001 OHSAS04016/079
TIS 18001 OHS01013/028



CUPRINOL

Cuprinol Decking Stain

Woodstain Matt Finished



Cuprinol Teak Oil is a specially formulated oil-base treatment for bare teak and similar hardwoods. Teak Oil gives hardwoods a rich natural finish and replaces the natural oils lost by weathering or hard wear which will cause the grey wood surface. Teak Oil is ideal for garden furniture and for matt-finished interior and exterior hardwood furniture.

Technical Information & Paint Film Properties

Type of Paint	Woodcare
Finish	No film
Pack size	3.5 Liters
Colour Offer	Clear
Touch Dry	At least 4 Hours
Recoat Dry	10 – 12 hours
Theoretical Coverage	15 – 20 Sq.m./coat/liters

*Coverage is theoretical value and may differ from real application +-20%

Application

Application Method	Brush or Spray
Mixing Ratio	If needs, thin down with ICI Cuprinol Thinner for All Purpose. Not more than 5% for brushing are allowable to appropriate viscosity
Cleaning Up	Clean all equipment while still wet with ICI Cuprinol Thinner for All Purposes

Application System

Surface Preparation : Wooden Surface

- *Pretreated Timber* Surface should be clean, dry and free from surface coating and grease before application. Moisture not over 14%.
- *Unpretreated Timber* Treat with a suitable wood preserver(non-bituminous wood preservative) and allow to dry 2-5 days before applying ICI Cuprinol Woodstain for Hardwoods. Wipe with ICI Cuprinol Thinner for All Purposes (T850-350) to remove any natural oils/resins, if necessary.
- *New/Bare Wood* Completely remove all gray wood by staining back to clean and sound wood.
- *Weathered Wood* Sand off or use hot air blower to strip existing coatings to condition of bare wood. Then treated are bare wood. Chemical stripper or paint remover is not recommended. The surface must be rinsed off with suitable solvent to clean sound wood.
- *Painted or Varnished Wood* Wash and scrub with ICI Cuprinol Thinner for All Purpose(T850-350) to remove dirt and grease and alert to dry.
- *Sound Woodstain Wood* All nailing must be galvanized or stainless nail.
- *Exterior Timber or Seaside Environmental*

Coating

Stir thoroughly before and occasionally during use. Brush on evenly along the grain by planning the continuity of the paint area to avoid overlap. Do not load brush heavily. Apply the first coat liberally, wipe off any surplus with a clean dry cloth. For exterior wood apply not more than 3 coats, for interior wood apply not more than 2 coats. Normally the maximum 3 coats is recommended. Ensure the first is dry before recoating. Do not apply before, during or after raining and high humidity condition. Recommend to apply the first coat of paint before do woodwork and the next coat after woodwork is done for consistency of colour.



ISO 9001 QMS03026/630
ISO 14001 EMS05021/198
OHSAS 18001 OHSAS04016/079
TIS 18001 OHS01013/028

The information in this datasheet is given to the best of our knowledge based on laboratory testing and for use recommendation. As the product is often used under conditions beyond our control, the company cannot guarantee anything only the quality of the product.

AkzoNobel Paints (Thailand) Ltd. (Former ICI Points (Thailand) Ltd.) 34/5 Moo 1 Choeng Watana Road, Klongklue, Pakkred Nonthaburi 11120
Customer Service : Telephone (662) 572-8888 Fax (662) 572-8889. www.dulux.co.th, www.facebook.com/duluxthailand