



# ดูลักซ์ เวเธอร์ชีลด์ โมลด์วอช

## น้ำยากำจัด และยับยั้งเชื้อรา และตะไคร่น้ำ



น้ำยากำจัด และยับยั้งเชื้อราและตะไคร่น้ำ ดูลักซ์ เวเธอร์ชีลด์ โมลด์วอช สูตรประสิทธิภาพ ที่ใช้ในการกำจัดเชื้อราและตะไคร่น้ำบนผนังได้อย่างหมดจด สามารถแทรกซึมเข้าไปตามรูพรุนของผนังได้ลึกมากกว่า อีกทั้งยังป้องกันการเจริญเติบโตของเชื้อราที่ไม่พึงประสงค์ ช่วยให้สีทับหน้าคงทนยาวนาน ปลอดภัยต่อการใช้งาน ไม่มีผลกระทบต่อการยึดเกาะของฟิล์มสี

### คำแนะนำเพิ่มเติม

เพื่อประสิทธิภาพสูงสุดควรใช้คู่กับผลิตภัณฑ์ดูลักซ์ เวเธอร์ชีลด์อื่น ๆ ตามความเหมาะสมของแต่ละสภาพพื้นผิวในทุกๆ ชั้นตอนของระบบการทาสี

- สีทับหน้า ดูลักซ์ เวเธอร์ชีลด์ อัลติมา แบบกึ่งเงา หรือ เนียน
- สีรองพื้นปูนกันด่าง ดูลักซ์ เวเธอร์ชีลด์ ซูเปอร์ไพรเมอร์

### ข้อมูลทางเทคนิคและคุณสมบัติของฟิล์มสี

ประเภทสี	น้ำยากำจัดเชื้อรา และตะไคร่น้ำ
ลักษณะฟิล์มสี	สีใส
ขนาดบรรจุ	3 ลิตร
ระยะเวลาแห้งสัมผัส	2 – 4 ชั่วโมง
การครอบคลุมพื้นที่ตามทฤษฎี	10 – 20 ตร.ม. / เทียว / ลิตร
*พื้นที่ครอบคลุมเป็นค่าทางทฤษฎี อาจแตกต่างจากการใช้งานจริงไม่เกิน 20%	

### วิธีการใช้งาน

วิธีการใช้งาน	ทาด้วยแปรง
การผสมก่อนใช้งาน	ใช้ได้ทันทีโดยไม่ต้องผสม

### ระบบการทาสี

ก่อนการทาสีทุกครั้ง พื้นผิวจะต้องแห้ง สะอาด ปราศจากฝุ่นละออง เศษซีเมนต์ คราบไขมัน และสิ่งสกปรกต่างๆ หากมีรอยแตกร้าวกว้างไม่เกิน 1 มม. ให้ซ่อมด้วยสีโป๊ว ดูลักซ์ อะคริลิก ฟิลเลอร์ 1040 ชัดแต่งให้เรียบ หากต้องการเพิ่มความเนียนเรียบให้กับพื้นผิว หรือปรับซ่อมผิวคอนกรีตที่มีปัญหา ให้ฉาบทั้งผนังด้วย ดูลักซ์ สมูทโอเวอร์ แล้วขัดแต่งให้เรียบและให้แน่ใจว่าผนังไม่มีรอยรั่วซึมของน้ำ เพื่อป้องกันฟิล์มสีโป๊พองภายหลัง

#### ขั้นที่ 1 การเตรียมพื้นผิว

ขูดลอกสีเดิมที่เสื่อมสภาพหรือหลุดล่อนออกก่อนทาน้ำยากำจัดและยับยั้งเชื้อรา และตะไคร่น้ำ ดูลักซ์ เวเธอร์ชีลด์ โมลด์วอช ด้วยแปรงให้ทั่วบริเวณ โดยเฉพาะจุดที่มีการแพร่เชื้อรา และตะไคร่น้ำ ทิ้งให้แห้ง 24 ชั่วโมง แล้วล้างออกด้วยน้ำสะอาด หรือขัดด้วยแปรง ก่อนทาสีทุกครั้ง ต้องล้างทำความสะอาดพื้นผิวให้ปราศจากฝุ่นละออง เศษซีเมนต์ คราบไขมัน และสิ่งสกปรกต่างๆ หรืออาจใช้กระดาษทรายขัดผิว ออกให้หมดก่อน ซ่อมแซมตกแต่งรอยแตก ร้าวบนพื้นผิวด้วยสีโป๊วดูลักซ์ อะคริลิก ฟิลเลอร์ 1040 ชัดแต่งให้เรียบ

การขัดแห้งด้วยกระดาษทราย การตัดด้วยเปลวไฟ และ/หรือการเชื่อมบนฟิล์มสีที่แห้งแล้ว จะทำให้เกิดฝุ่นและ/หรือละอองและ/หรือควันที่เป็นอันตราย หากเป็นไปได้ควรใช้วิธีขัดน้ำ หากไม่สามารถหลีกเลี่ยงการสัมผัสโดยมีระบบระบายอากาศเฉพาะที่ได้ ควรสวมอุปกรณ์ป้องกันระบบทางเดินหายใจที่เหมาะสม

#### ขั้นที่ 2 การทาสีรองพื้น

- พื้นผิวปูนใหม่ไม่เคยทาสี หรือทาสีแล้วสียังอยู่ในสภาพดี

ทาสีรองพื้นปูนใหม่กันด่าง ดูลักซ์ เวเธอร์ชีลด์ ซูเปอร์ไพรเมอร์ จำนวน 1 เทียว ทิ้งให้แห้งอย่างน้อย 2 ชั่วโมง ก่อนทาสีทับหน้า

- พื้นผิวปูนเก่าที่เสื่อมสภาพ เป็นปูนขอลังหรือไม้สังเคราะห์ ไซเบอริซีเมนต์หรือพื้นผิวที่มีการใช้วัสดุฉนวน

ทาน้ำยรองพื้นปูนเก่า เพื่อเสริมสภาพ ดูลักซ์ มาซีล A200-743 จำนวน 1 เทียว ทิ้งให้แห้งอย่างน้อย 10-12 ชั่วโมง ก่อนทาสีทับหน้า

#### ขั้นที่ 3 การทาสีทับหน้า

ทาสีทับหน้าด้วย สีน้ำสำหรับภายนอก และ/หรือ สีน้ำสำหรับภายในตระกูล ดูลักซ์ อย่างน้อย 2 เทียว โดยทิ้งระยะห่างระหว่างสีที่ทาชั้นแรกและชั้นถัดไป ประมาณ 30 นาที – 2 ชั่วโมง



CM-A2916-2016/11370



ISO 9001 QMS03026/630  
ISO 14001 EMS05021/198  
OHSAS 18001 OHSAS04016/079  
TIS 18001 OHS01013/028



# Dulux Weathershield Mould Wash Fungus & Algae Wash



Dulux Weathershield Mould Wash kills fungus and algae on surfaces effectively, without affecting the adhesion and colour of subsequent paint coats. It penetrates deeper and better into the surfaces to stop fungus and algae growth for long lasting quality of top coat. It is a ready-for-use aqueous chemical wash, which is low in odour, non-staining, and completely biodegradable, suitable to both interior and exterior surfaces

## ADDITIONAL NOTE

For perfect result, use in conjunction with other Dulux Weathershield products throughout paint system.

- Dulux Weathershield Ultima
- Dulux Weathershield SuperPrimer

## Technical Information & Paint Film Properties

Type of Paint	Fungus and Algae Killer
Finish	Clear amber liquid
Pack size	3 Litres
Touch Dry	2 - 4 Hours
Theoretical Coverage	10 – 20 sq.m./litre

\*Coverage is theoretical value and may differ from real application +20%

## Application System

Application Method	Brush
Mixing Ratio	Ready to use

## Application System

Surfaces must be dry, clean, and free from dirt, loose materials, and grease. If there is a crack of no more than 1 mm, repair with Dulux Acrylic Filler 1040 as surfaces must be sealed to prevent water leaking to the paint films which would causes film bubble and peeling problems. If the smoothness is needed, apply the wall with Dulux Smoothover acrylic skim-coat.

### Step 1: Surface Preparation

Remove old paints before brushing Dulux Weathershield Mould Wash throughout the surface, especially the area affected by fungus and algae. Allow 24 hours drying before washing with clean water or brushing. Surfaces must be dry, clean and free from dirt and loose materials. Repair all cracks with Dulux Acrylic Filler 1040. All surfaces must be sealed and prevented water to leak to the paint films to avoid film bubble or peeling.

Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet [sanding]/ [flattening] should be used wherever possible. If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used.

### Step 2: Priming

- *New masonry or previously painted in good condition* : Apply 1 coat of Dulux Weathershield SuperPrimer. Allow at least 2 hours drying before applying topcoat.

- *Previously painted, powdery surfaces, fiber-cement or skim coat surfaces* : Apply a thin coat of Dulux Maseal A200-743 and allow 10-12 hours drying prior applying top coat.

### Step 3: Topcoat

: Apply at least 2 coats of any Dulux exterior paints. Allow 2 - 3 hours between coats. Diluted with clean water only.



CM AZN JV-2016.11.13.70



ISO 9001 QMS03026/630  
ISO 14001 EMS05021/198  
OHSAS 18001 OHSAS04016/079  
TIS 18001 OHS01013/028

The information in this datasheet is given to the best of our knowledge based on laboratory testing and for use recommendation. As the product is often used under conditions beyond our control, the company cannot guarantee anything only the quality of the product.

AkzoNobel Paints (Thailand) Ltd. (Former ICI Paints (Thailand) Ltd.) 34/5 Moo 1 Chaeng Watana Road, Klongklue, Pakkred Nonthaburi 11120  
Customer Service : Telephone (662) 572-8888 Fax (662) 572-8889, www.dulux.co.th, www.facebook.com/duluxthailand