

# VIVELOCK GLOSS

## Enamel Paint – Direct to Rust



### DESCRIPTION

**VIVELOCK GLOSS** is a special gloss paint, that is applied directly on corroded metallic surfaces, with no need for anticorrosive primer. **VIVELOCK GLOSS** is the easy and effective solution against corrosion, for the protection of new or old metallic surfaces such as doors, railings and any ironwork. It exhibits strong adhesion, maximum hardness and very good working and leveling properties. It provides excellent antirust protection and attractive finish with long term gloss and colour retention.

**Direct to rust**

### PRODUCT INFORMATION

**Strong Adhesion**

**Type:** Enamel paint based on specially modified alkyd resins.

**Specific gravity:** 0,93 - 1,14 gr/cm<sup>3</sup>(ELOT 523), depending on shade

**Viscosity:** 10 - 12 P (ROTOTHINNER DIN 51550, 25 OC)

**Application method:** Brush or spray gun

**Thinning:** Use with brush: Ready for use. If thinning is necessary, add up to 3% v/v VIVECHROM's BRUSH SOLVENT. Use with spray gun: Up to 15% v/v with VIVECHROM's SPRAY GUN SOLVENT

**Spreading rates:** About 4,5 - 9 m<sup>2</sup> per litre on previously prepared surfaces, for 100 - 50 µm dry film thickness respectively

**Drying times:** Touch dry after 4 hours and can be recoating the next day (24 hours). Drying time depends on weather conditions (humidity, temperature)

**Colours:** It is available in white and 15 shades from factory colourcard

#### VOC (Volatile Organic Compounds)

EU limit value for this product category  
A/i one-pack performance coatings: 500g/l (2010).  
This product contains max 499g/l.





# VIVELOCK GLOSS

## Enamel Paint – Direct to Rust

### SURFACE PREPARATION

- Surfaces must be clean and dry.
- Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet sanding/flattening should be used wherever possible. If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used.

### APPLICATION

- Application with brush:  
Ready for use. Apply 2 thick coats of VIVELOCK GLOSS.
- Application with spray gun:  
Apply 3 coats of VIVELOCK GLOSS thinned up to 15% with Spray Gun Solvent.
- Ensure that all corners and difficult points are adequately covered, and that there are no pinholes which allow moisture to penetrate.

### AFTER USE

Remove as much paint as possible from brushes and rollers before cleaning • Clean brushes and equipment with BRUSH SOLVENT by Vivechrom.

### HEALTH, SAFETY & ENVIRONMENTAL INFORMATION

WARNING. Contains- Naphtha (petroleum), hydrotreated heavy • Flammable liquid and vapour • May cause drowsiness or dizziness • Keep out of reach of children • If medical advice is needed, have product container or label at hand • Do not get in eyes, on skin, or on clothing • Keep away from heat, sparks, open flames and hot surfaces • No smoking. Keep container tightly closed • Do not get in eyes, on skin, or on clothing • Call a POISON CENTER or doctor if you feel unwell • Keep cool • Do not empty into drains • Dispose of contents and container in accordance with all national regulations • Repeated exposure may cause skin dryness or cracking • Contains 2-Butanone oxime. May produce an allergic reaction.  
Poison Tel Center: 210 7793777.



**STIR WELL BEFORE USE - PROTECT FROM FROST  
DO NOT APPLY AT TEMPERATURES UNDER 10°C.**



[www.vivechrom.gr](http://www.vivechrom.gr)